



# JAFLOC CP59

## Polymer Flocculant

### FEATURES

- Water conditioning
- Compatible with mineral coagulants
- Removal of colloidal material

### AREAS OF USE

- Industrial water treatment
- Waste water treatment
- Municipal water treatment

### DESCRIPTION

JAFLOC CP59 is a high density charge polyacrylamide powder used for waste water flocculation in various industries.

### DIRECTIONS FOR USE

The dose rate of JAFLOC CP59 will depend upon a number of factors. For assessment before use, please consult your Jasol representative.

### SAFETY INFORMATION

JAFLOC CP59 is NOT classified as Hazardous according to the GHS.  
 JAFLOC CP59 is NOT classified as Dangerous Goods according to the ADG Code (7<sup>th</sup> Ed).  
 JAFLOC CP59 is NOT a Scheduled Poison according to the SUSMP.

#### FIRST AID INFORMATION

For advice in an emergency, contact **Poisons Information Centre Australia (phone 13 11 26)** or **a doctor at once**. If swallowed do NOT induce vomiting. Wash out mouth thoroughly with water. If in eyes, hold eyelids apart and flood with water for at least 15 minutes. Seek medical attention if irritation persists.

**24 HOUR TOLL FREE EMERGENCY PHONE NO: 1800 629 953**

### PRODUCT ENQUIRIES

Customer Service: **1800 334 679**  
[jasolcsteam@gwf.com.au](mailto:jasolcsteam@gwf.com.au)

For further information regarding product safety and handling, refer to the Safety Data Sheet and product label.

### PHYSICAL & CHEMICAL PROPERTIES

<b>FORM</b>	Granular Powder
<b>COLOUR</b>	White
<b>MESH SIZE (% &gt;10 mesh)</b>	2
<b>MESH SIZE (% &lt;100 mesh)</b>	6
<b>IONIC CHARACTER</b>	Cationic
<b>CHARGE DENSITY</b>	High
<b>MOLECULAR WEIGHT</b>	Ultra High
<b>pH</b>	2.5-4.5 (@5 g/L)
<b>Approx. BULK DENSITY</b>	0.8
<b>MAX. CONCENTRATION</b>	5 g/L
<b>DISSOLUTION TIME in DI water</b>	90 minutes
<b>STABILITY OF D.I. SOLUTIONS</b>	1 day
<b>RECOMMENDED WORKING CONC</b>	3 g/L
<b>STORAGE TEMPERATURE</b>	0-35°C
<b>SHELF LIFE</b>	24 months

15kg  
 2144070

